

Technical Data Sheet

Fabric Type BAS 115.1000.P

suter-kunststoffe ag
swiss-composite.ch

CH-3312 Fraubrunnen 031 763 60 60 Fax 031 763 60 61
 www.swiss-composite.ch info@swiss-composite.ch

Woven fabric for composite applications, is entirely made of 100% BCF (basalt continuous filament) yarn.

The first code 115 is the surface density in g/m²

The second code 1000 is the width of the fabric in mm. The third code indicates the weave.

The silane sizing B08 is selected, which has components to ensure elasticity of the yarn during textile processes. B08 allows good compatibility with epoxy, vinylester and polyester resins systems.

Property	Standard/Method	Unit	Value	Tolerance
Base material				
Density of unsized filament matl*		kg/dm ³	2.70	+ 5%
Moisture content of basaltic rock*		%	0.1	+ 0.05
Melting point*		°C	1350	+ 100
Fabric				
Specific surface weight**	ISO 3374:2000	g/m ²	115	
Weave type**			Plain	
Yarn density/type**:				
- warp		ends/cm	8.5	
- weft		ends/cm	8.0	
- linear density		tex	68	
Width**	ISO 5025:1997	mm	1000	-0/+20
Thickness	ISO 4603:1993	mm	0.1	
Sizing type**			B08	
Breaking load:	ISO 4606:1995 – Type II			
- warp		N/25mm	>1156	
- weft		N/25mm	>1088	
Continuous temperature range		°C	- 250°C 350°C with stress 550°C w/o stress 1200°C fire barrier	
Moisture content (fabric)	ISO 3344:1997	%	<0.3	
LOI, also sizing content**	ISO 1887:1995***	%	0.4 – 0.6	
Combustibility	NF P92-503:1995	M0	Pass	
UV stability	ISO 105-B02		6	
Colour fastness	ISO 1005-BX12		6	

* data from literature

**properties given on the "Quality Report" coming with each product delivery

*** after drying according ISO 3344:1997

Packaging

Fabric length is approximately 500 lm per roll. Other length on request. Roll tube has internal diameter of 150 mm. Identification label. Standard packing.

Product Stability:

Products have not been designed for full external exposure conditions and cannot be guaranteed for use in such situations. However, these products have considerable tolerance to damp conditions and occasional water immersion. After drying out, the product will give the same level of performance as the original sample.

Stability over time:

Said products not being subjected to excessive heat, wear and abrasion, all evidence obtained to date indicates that their performance should not significantly change over a significant period of time.

It is the responsibility of the developer of the end-product, finished device or system to test its performance in the end-application.