

TECHNICAL DATASHEET



Article: Style 761
 Setting [threads/cm]: 6,1/7,0
 Weave: Plain
 Finish: loomstate

suter-kunststoffe ag
swiss-composite.ch
 CH-3312 Fraubrunnen 031 763 60 60 Fax 763 60 61

Construction:	Warp	Weft
Material:	Carbon	Glas
Yield:	200 tex	68 tex

Technical Data	Standard		Unit	Target	+/-	Tolerance
Fibre density 1) 3)		Warp	g/cm ³	n.G.	+/-	n.G.
		Weft	g/cm ³	n.G.	+/-	n.G.
Linear density 1)		Warp	tex	200	+/-	10
		Weft	tex	68	+/-	4
Twist 1)		Warp	T/m		+/-	
		Weft	T/m		+/-	
Setting	DIN EN 1049 T2 4)	Warp	thr./cm	6,1	+/-	0,1
		Weft	thr./cm	7,0	+/-	0,3
Weight	DIN ISO 12127 4)		g/m ²	170	+/-	8
Dry Weight	DIN EN ISO 3344 4)		g/m ²	170	+/-	8
Moisture content	DIN EN ISO 3344 4)		%	0,5		
Thickness 2)	DIN ISO 5084 4)		mm	0,25	+/-	0,03
Width	DIN EN 1773 4)		cm	as ordered	+/-	1

1) or n.G.: depending on order and yarn specification

2) approximate value, not for release

3) no measure, certified by supplier

4) according to DIN...

Remark:

The values describe the properties of the fabric based on a limited production period.

Date 07.10.2015	QM Sybille Büscher	This datasheet does not include revision service.
--------------------	-----------------------	---