



Technische Daten/Technical data

Kohlegelege 750 g/m²/ Non-crimp fabric 750 g/m²

FABRIC CONSTRUCTION

FIBRE TYPE: Carbon
CONSTRUCTION: 0/-45/+45
FABRIC WEIGHT: 749 gsm +/- 5%
FIBRE USED: T620SC-24k-50C

STITCHING FIBRE

STITCHING THREAD: Textured Polyester
STITCH DTex: 78
STITCH GAUGE: 5.0 gg
STITCH LENGTH: 2.12 mm
STITCH TYPE: Pillar
STITCH WEIGHT: 7 gsm

PLY CONSTRUCTION

+45 Ply LAYER C


FIBRE SPECIFICATION: T620SC-24k-50C
FIBRE TEX: 1850 tex
GAUGE: 2.1 gg
PLY WEIGHT: 216 gsm

0 Ply

FIBRE SPECIFICATION: T620SC-24k-50C
FIBRE TEX: 1850 tex
GAUGE: 4.25 gg
PLY WEIGHT: 310 gsm

-45 Ply LAYER A

FIBRE SPECIFICATION: T620SC-24k-50C
FIBRE TEX: 1850 tex
GAUGE: 2.1 gg
PLY WEIGHT: 216 gsm



Alle Informationen, Empfehlungen oder Ratschläge seitens der R&G Faserverbundwerkstoffe GmbH erfolgen nach bestem Wissen und Gewissen. Sie gelten als unverbindliche Hinweise und enthalten weder ausdrückliche noch stillschweigende Zusicherungen noch eine Garantie bestimmter Eigenschaften. Bei den angegebenen Eigenschaftskennwerten handelt es sich um typische Werte. Empfehlungen oder Ratschläge beschreiben unsere Produkte und mögliche Anwendungen in genereller oder beispielhafter, aber nicht auf den Einzelfall bezogener Weise. Im Zuge der ständigen technischen Weiterentwicklung und Verbesserung unserer Produkte können sich Veränderungen in den Kennwerten, Texten und Graphiken ergeben; ein besonderer Hinweis auf eine evtl. Veränderung erfolgt nicht. Der Kunde prüft eigenverantwortlich unsere Produkte in Hinblick auf ihre Eignung für die beabsichtigten Verfahren und Zwecke sowie ihre entsprechende Verarbeitbarkeit, da die technischen Einsatzmöglichkeiten unserer Produkte zahlreich und je nach Fall sehr unterschiedlich sind. Sie entziehen sich daher unseren Kontrollmöglichkeiten und liegen ausschließlich im Verantwortungsbereich des Kunden. Etwaige Schutzrechte sowie bestehende Gesetze und Bestimmungen sind vom Abnehmer bzw. Anwender in eigener Verantwortung zu beachten. Die Veröffentlichung ist keine Lizenz und beabsichtigt nicht die Verletzung irgendwelcher Patente. Poxysystems® ist ein registriertes Warenzeichen von R&G

All information, recommendations, and advice on the part of R&G Faserverbundwerkstoffe GmbH are published to the best of our knowledge and belief. They are noncommittal and contain neither explicit nor tacit assurance or warranty of particular properties. The values specified for properties are typical figures. Recommendations or advice serve to describe our products and possible applications in a general or exemplary, but not specifically individual manner. In the course of the constant technical advancement and improvement of our products there may be changes to the characteristic values, copy, and diagrams; no specific reference is made to any such change. Owing to our products' wide and highly diverse range of potential applications far beyond any of our attempts to analyse, the customer alone is responsible for examining our products' suitability for the respective processes and purposes and their respective processability. All and any protective rights and the applicable laws, terms, and conditions must be observed by the buyer or user of our products at their own responsibility. Publication is not a licence and does not intend the violation of any patents. Poxysystems® is a registered trademark of R&G.