

TECHNICAL DATASHEET



Article: Style 635-1
Setting [threads/cm]: 6,5/6,0
Weave: Twill 3/1
Finish: loomstate

suter-kunststoffe ag
swiss-composite.ch
 CH-3312 Fraubrunnen 031 763 60 60 Fax 763 60 61

Construction:	Warp	Weft
Material:	Aramid+Carbon	Aramid+Carbon
Yield:	127 + 200 tex	127 + 200 tex

Technical Data		Unit	Target	+/-	Tolerance
Fibre density ^{1) 3)}	Warp	g/cm³	-/n.G.	+/-	-/n.G.
	Weft	g/cm³	-/n.G.	+/-	-/n.G.
Linear density ¹⁾	Warp	tex	130/200	+/-	6/10
	Weft	tex	130/200	+/-	6/10
Twist ¹⁾	Warp	T/m		+/-	
	Weft	T/m		+/-	
Setting	Warp	thr./cm	6,5	+/-	0,2
	Weft	thr./cm	6,0	+/-	0,2
Weight		g/m²	210	+/-	10
Dry Weight		g/m²	210	+/-	10
Moisture content		%	2,5		
Thickness ²⁾		mm	0,46	+/-	0,05
Width		cm	as ordered	+/-	1

1) or n.G.: depending on order and yarn specification

2) approximate value, not for release

3) no measure, certified by supplier

Remark:

The values describe the properties of the fabric based on a limited production period.

Date 21.05.2015	QM Sybille Büscher	This datasheet does not include revision service.
---------------------------	------------------------------	--