

TECHNICAL DATASHEET



Article: Style 447
Setting [threads/cm]: 4,0/4,0
Weave: Plain
Finish: loomstate

suter-kunststoffe ag
swiss-composite.ch
 CH-3312 Fraubrunnen 031 763 60 60 Fax 763 60 61

Construction:	Warp	Weft
Material:	Carbon	Carbon
Yield:	200 tex	200 tex

Technical Data		Unit	Target	+/-	Tolerance
Fibre density ^{1) 3)}	Warp	g/cm ³	n.G.	+/-	n.G.
	Weft	g/cm ³	n.G.	+/-	n.G.
Linear density ¹⁾	Warp	tex	200	+/-	10
	Weft	tex	200	+/-	10
Twist ¹⁾	Warp	T/m		+/-	
	Weft	T/m		+/-	
Setting	Warp	thr./cm	4,0	+/-	0,2
	Weft	thr./cm	4,0	+/-	0,2
Weight		g/m ²	160	+/-	-4/+6
Dry Weight		g/m ²	160	+/-	-4/+6
Moisture content		%	0,5		
Thickness ²⁾		mm	0,30	+/-	0,04
Width		cm	as ordered	+/-	1

1) or n.G.: depending on order and yarn specification

2) approximate value, not for release

3) no measure, certified by supplier

Style 447T = Style 447 with tracer yarn as ordered

Remark:

The values describe the properties of the fabric based on a limited production period.

Date 09.04.2015	QM Sybille Büscher	This datasheet does not include revision service.
--------------------	-----------------------	---