

TECHNICAL DATASHEET



Article: Style 461
Setting [threads/cm]: 6,0/6,0
Weave: Plain
Finish: loomstate

suter-kunststoffe ag
swiss-composite.ch
 CH-3312 Fraubrunnen 031 763 60 60 Fax 763 60 61

Construction:	Warp	Weft
Material:	Carbon	Carbon
Yield:	67 tex	67 tex

Technical Data		Unit	Target	+/-	Tolerance
Fibre density ^{1) 3)}	Warp	g/cm ³	n.G.	+/-	n.G.
	Weft	g/cm ³	n.G.	+/-	n.G.
Linear density ¹⁾	Warp	tex	67	+/-	4
	Weft	tex	67	+/-	4
Twist ¹⁾	Warp	T/m		+/-	
	Weft	T/m		+/-	
Setting	Warp	thr./cm	6,0	+/-	0,3
	Weft	thr./cm	6,0	+/-	0,3
Weight		g/m ²	80	+/-	4
Dry Weight		g/m ²	80	+/-	4
Moisture content		%	0,5		
Thickness ²⁾		mm	0,15	+/-	0,03
Width		cm	as ordered	+/-	1

1) or n.G.: depending on order and yarn specification

2) approximate value, not for release

3) no measure, certified by supplier

Remark:

The values describe the properties of the fabric based on a limited production period.

Date 10.04.2015	QM Sybille Büscher	This datasheet does not include revision service.
----------------------------------	-------------------------------------	--