

**Technical Data Sheet** Most recent revision date:



1/16/2019

# EPIKOTE<sup>™</sup> Resin TRAC 06150 (Formerly named EPIKOTE™ Resin 05475) EPIKURE<sup>™</sup> Curing Agent TRAC 06150 (Formerly named EPIKURE™ Curing Agent 05443) HELOXY<sup>™</sup> Additive TRAC 06805

(Formerly named HELOXY<sup>™</sup> Additive 112)

# **Product Description**

EPIKOTE<sup>™</sup> Resin TRAC 06150 is a medium viscosity epoxy resin. EPIKURE<sup>™</sup> Curing Agent TRAC 06150 is a low viscosity amine hardener. HELOXY<sup>™</sup> Additive TRAC 06805 is a silicone- and wax-free internal mold release agent.

## **Application Areas/Suggested Uses**

Low viscous resin system designed for RTM applications with excellent wetting and adhesion characteristics on glass-, carbon- or aramid-fibers. Benefits of this system are a low viscosity during infusion (2 min at 100°C < 150mPas) and a short curing cycle, which allows an early de-molding (e.g. 5 min at 120°C).

The EPIKOTE™ Resin TRAC 06150 with EPIKURE™ Curing Agent TRAC 06150 system is compatible with the internal mold release agent HELOXY™ Additive TRAC 06805, which can be added in a recommended amount of about 1 – 2 phr.

Typical suggested uses include but are not limited to the production of structural automotive parts such as parts of the frame or chassis, floor panels, bulkheads monocoque structure, and exterior and visible structural parts such as rooftops, pillars, heads and deck lids.

## **Benefits**

- Low viscosity during injection.
  - Easy to process due to thermolatent behavior:
    - Long infusion time (90 sec at 120°C)
    - Fast glass transition temperature (T<sub>G</sub>) development 0
    - Short curing cycle (e.g. 5 min at 120°C)  $\circ$
- Excellent fiber wetting properties.
- Excellent thermal and mechanical performance.
- Good surface quality for painted parts.

## page 1 of 5

The information provided herein was believed by Hexion Inc. and its affiliated companies ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION, except that the product shall conform to Hexion's specifications at the time of delivery.

Nothing contained herein constitutes any offer for the sale of any product. © 2015 Hexion Inc. All rights reserved.

® and TM denote trademarks owned or licensed by Hexion Inc.

Varziner Straße 49 47135 Duisburg-Meiderich

Postfach 120552 47125 Duisburg

Germany

www.hexion.com



## **Typical Properties**

## EPIKOTE™ Resin TRAC 06150

Property	Unit	Value	Test Method
Viscosity at 25°C Color Gardner Refractive index at 25°C Density at 20°C	mPa·s kg/l	8750 – 11250 0 - 1 1.569 - 1.575 1.15 – 1.19	DIN 53015 ISO 4630 DIN 51423 ISO 2811
Delivery form		liquid	

## EPIKURE™ Curing Agent TRAC 06150

Property	Unit	Value	Test Method
Viscosity at 25°C	mPa⋅s	5 - 25	DIN 53015
Refractive index at 25°C		1.490 – 1.494	DIN 51423_2
Color Gardner		0 – 2	ISO 4630
Density at 20°C	kg/l	0.95 – 0.99	ISO 2811
Delivery form	_	liquid	

## HELOXY<sup>™</sup> Additive TRAC 06805

Property	Unit	Value	Test Method
Viscosity at 30°C Refractive index at 25°C	mPa·s	500 - 900 1,4565 – 1,4605	DIN 53015 DIN 51423_2
Density at 20°C Appearance Delivery form	kg/l	1.01 – 1.05 yellow/brown liquid	ISO 2811

# page 2 of 5

The information provided herein was believed by Hexion Inc. and its affiliated companies ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION, except that the product shall conform to Hexion's specifications at the time of delivery.

Nothing contained herein constitutes any offer for the sale of any product. © 2015 Hexion Inc. All rights reserved. © and TM denote trademarks owned or licensed by Hexion Inc.

Varziner Straße 49 47135 Duisburg-Meiderich

Postfach 120552 47125 Duisburg

Germany

www.hexion.com

02/2015



1/16/2019

## **Processing Details**

## Mixing ratio

EPIKOTE™ Resin TRAC 06150	100	parts by weight
EPIKURE™ Curing Agent TRAC 06150	24	parts by weight
HELOXY™ Additive TRAC 06805	1-2	parts by weight

## Mixing tolerance

The maximum allowable mixing tolerance (resin & hardener) is  $\pm 1$  pbw, but it is particularly important to preserve the recommended mixing ratio as accurately as possible. Incorrect dosing of the hardener is not an appropriate approach to accelerate or retard the reaction; rather it will lead to an incomplete cure. The reaction speed can be properly adjusted by changing the processing temperature, as indicated below. Resin and hardener must be mixed very thoroughly. Mix until no clouding is visible, pay special attention to the walls and the bottom of the mixing container.

#### Material preheating

To optimize the process a preheating of the components is recommended.

EPIKOTE™ Resin TRAC 06150	60-80	°C
EPIKURE™ Curing Agent TRAC 06150	RT-30	°C
HELOXY™ Additive TRAC 06805	25-30	°C

## **Processing Temperature**

The system exhibits good processing in the temperature range between 80 and 140 °C, and full curing can typically be achieved in 5 minutes cure at 120°C. Higher processing temperatures are possible but will shorten the pot life. A rise in temperature of 10 °C reduces the pot life by approx. 50%. Different temperatures during processing have no significant effect on the mechanical properties of the hardened product.

Do not mix large quantities at elevated processing temperatures as this can lead to an uncontrolled exothermic reaction where the mixture may heat up very quickly to more than 200 °C in the mixing container.

Processing Data		Unit	Value
Viscosity of formulation	at 25°C	mPa⋅s	1200 ± 100
	at 80°C	mPa⋅s	$30 \pm 5$
	at 100°C	mPa⋅s	13± 3
Pot life	at 25°C	min	120 ± 10
Gel time	at 80°C	S	330 ± 30
	at 100°C	S	210 ± 30
	at 120°C	S	150 ± 30
	at 140°C	S	90 ± 30
Viscosity increase	at 80°C	mPa⋅s	47/63/100
after 60s / 120s / 180s	at 100°C	mPa⋅s	33/123/1402
	at 120°C	mPa⋅s	40/865/>100000
	at 140°C	mPa⋅s	20070/>100000/-

## page 3 of 5

The information provided herein was believed by Hexion Inc. and its affiliated companies ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION, except that the product shall conform to Hexion's specifications at the time of delivery.

ACCURACY OF ANY INFORMATION PROVIDED BY HEXION, except that the product shall conform to Hexion's specifications at the time of delivery. Nothing contained herein constitutes any offer for the sale of any product. © 2015 Hexion Inc. All rights reserved.

® and TM denote trademarks owned or licensed by Hexion Inc.

Postfach 120552 47125 Duisburg

Varziner Straße 49 47135 Duisburg-Meiderich

Germany

www.hexion.com

02/2015



**Technical Data Sheet** Most recent revision date:

1/16/2019



# Typical Properties of the cured, non-reinforced system

Cast by hand; curing cycle: 5 min at 120°C

Properties	Unit	Value	Test Method
T <sub>G</sub> , DSC			DSC (10K/min)
Onset	°C	118 ± 2	
Midpoint	С°	124 ± 2	
Thermal expansion	ppm/K	< 75	ISO 11359-2
coefficient			
Tensile test at RT			DIN EN ISO 527-1
Tensile strength	MPa	85 ± 2	
Tensile modulus	MPa	2900 ± 100	
Elongation at break	%	6 - 8	
Bending test at RT			DIN EN ISO 178
Flexural strength	MPa	130 ± 5	
Flexural modulus	MPa	3000 ± 100	
Charpy impact at RT	mJ/mm²	24 ± 2	ISO 179
Fracture performance at RT			ISO 17281
Fracture toughness K <sub>1C</sub>	MPa√m	$0.75 \pm 0.05$	
Fracture energy G <sub>1C</sub>	J/m²	225 ± 5	
Water uptake (7d at 23°C)	%	< 0.4	DIN EN ISO 62
Total shrinkage at RT	Vol. %	< 4	Calculated DIN 16945
Hardness at RT	Shore D	85 - 86	DIN 53505-D
Density at 23°C	kg/l	1.151 – 1.155	DIN 53479 A

#### page 4 of 5

The information provided herein was believed by Hexion Inc. and its affiliated companies ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION, except that the product shall conform to Hexion's specifications at the time of delivery.

ACCURACY OF ANY INFORMATION PROVIDED BY HEXION, except that the product shall conform to Hexion's specifications at the time of delivery Nothing contained herein constitutes any offer for the sale of any product. © 2015 Hexion Inc. All rights reserved.

® and TM denote trademarks owned or licensed by Hexion Inc.

Varziner Straße 49 47135 Duisburg-Meiderich

Postfach 120552 47125 Duisburg

Germany

www.hexion.com



1/16/2019

## Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

EPIKOTE<sup>™</sup> Resin TRAC 06150 should be stored at room temperature in its carefully sealed original containers. Under these conditions, the shelf life is a minimum of three years from date of certification.

EPIKURE<sup>™</sup> Curing Agent TRAC 06150 should be stored at room temperature in its carefully sealed original containers, so that moisture is excluded. Under these conditions, the shelf life is a minimum of one year from date of certification. Care should be taken to avoid storage environments resulting in moisture contamination. Exposure to moisture will cause an increase in viscosity and reactivity, the degree of increase depending on the amount of moisture, which has been absorbed.

HELOXY<sup>™</sup> Additive TRAC 06805 should be stored at temperature between 10 and 35°C in its carefully sealed original containers, so that moisture is excluded. Under these conditions, the shelf life is a minimum of 6 months.

Before use, it is necessary to homogenize the material by shaking or stirring.

Occasionally, it is possible that the resin or the hardener crystallize at temperatures below 15°C. The crystallization is visible as a clouding or solidification of the content of the container. Before processing, the crystallization must be removed by warming up. Slow warming up to 50 - 60°C in a water bath or oven and stirring or shaking will clarify the contents in the container without any loss of quality. Use only completely clear products. Before warming up, open containers slightly to permit equalization of pressure. Caution during warm up! Do not warm up over open flame! While stirring up use safety equipment (gloves, eyeglasses, respirator equipment).

## **Contact Information**

For further Technical Inquiries on the properties and performance of this matrix system in reinforced composites. please contact us at our Customer Service Center +1 888 443 9466 4information@hexion.com or 4information.eu@hexion.com for EMEA or 4information.ap@hexion.com for Asia.

#### page 5 of 5

The information provided herein was believed by Hexion Inc. and its affiliated companies ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION, except that the product shall conform to Hexion's specifications at the time of delivery. Nothing contained herein constitutes any offer for the sale of any product.

© 2015 Hexion Inc. All rights reserved. ® and TM denote trademarks owned or licensed by Hexion Inc. Varziner Straße 49 47135 Duisburg-Meiderich

Postfach 120552 47125 Duisburg

Germany

www.hexion.com

02/2015