

# Technical Data Sheet

## EPIKOTE™ Resin 05390

### Product Description

EPIKOTE™ Resin 05390 is an epoxy-based powder binder that is applied as a hot-melt system to stabilize glass and/or carbon composite reinforcements and create fiber preforms.

### Application Areas/Suggested Uses

EPIKOTE™ Resin 05390 is a universal tool for various preforming applications with long shelf life, a softening temperature between 80 - 90°C, excellent application behavior and compatibility to epoxy resin matrices. EPIKOTE™ Resin is suitable to produce preforms for a broad range of composite parts such as automotive structural or exterior parts, composites for industrial and Wind-energy applications and mass transportation.

### Features and Benefits

- Good flow behavior at application temperature
- Very good compatibility with Epoxy resin systems.
- Reversible process of preform-forming in the temperature range of 80- 90 °C
- Very good processability via powder application on the fabric.

### Sales Specifications

Property	Value	Unit	Test Method
Particle Size Distribution Particles <12 µm	8 - 12	%	ISO 8130-1
Particle Size Distribution Particles < 200 µm	99.5	%	ISO 8130-1

### Typical Properties

Property	Value	Unit
Bulk Density	550 ± 50	kg/m³
Delivery Form	White Powder	
Softening Point	90 ± 15	°C

For further Technical Inquiries on the properties and performance of this preform binder matrix system, please contact us at TRAC@momentive.com or at our Customer Service Center at +1 888 443 9466 / 4information@momentive.com

### Safety, Storage & Handling

For information about safe handling of Epikote epoxy resins and Epikure Curing Agents please note the corresponding Safety Data Sheet.

EPIKOTE™ Resin 05390 can be stored at 20-25°C for at least 12 months in the carefully sealed original containers. By storing the powder under higher temperatures (above 30°C) particles may agglomerate and affect the processing.

EPIKOTE™ Resin 05390  
<https://www.hexion.com/en-US/product/epikote-resin-05390>

Generated: April 7, 2022  
Issue Date:  
Revision: 11/1/2012 12:00:00 AM

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.